

WIDOCRYL-Clear Varnish PM



Basis

Elasticised urethane-modified methyl methacrylate resin

Curing with hardener (at + 20,0 °C)

Rainproof after 30 min.
Walkable after 60 min.

Consumption

Approx. 600 - 800 g/m² on surfaces sprinkled with granite granules

Basic paint colour

Transparent

Packaging unit

10.00 kg

Min. working temperature

- 5 °C

Temperature resistance

- 30°C to + 90°C

Cleaning in fresh state

WIDOPAN-Cleaner

Storage

If container is kept closed and storage temperature held constantly below + 20°C, the product may be used for up to 6 months.

WIDOCRYL-Clear Varnish PM is used for sealing of the finished composite seal (laminare construction) of WIDOCRYL-Topsiegel SV /PM and the wearing surface of granite chippings.

WIDOCRYL-Clear Varnish PM is based on low-viscosity, elasticised methyl methacrylate resin.

Surface preparation

The surface to be sealed must be dry, clean and free from grease and dust. Surplus granite chippings must be brushed away or removed using an air blower before application of the clear varnish.

Mixing

Before adding the hardener, the WIDOCRYL-Clear Varnish PM has to be mixed thoroughly. The amount of hardener needed depends on the temperature. The mixing ratio is mentioned on the lid.

Further details, especially regarding hazard statements, security advices and measures in the event of fire can be found in the safety data sheet under sections 2, 4, 5, 6, 7 and 8.

Please also refer to our instructions on priming and our technical information sheets!