


WIDOCRYL-Roller coating



Basis

Methyl methacrylate resin

Pot life with hardener (at +20 °C)

approx. 10 min.

Consumption

approx. 1,0 kg/m²

Basic colour

Pebble grey (near RAL 7032)

Window grey (near RAL 7040)

Anthracite (near RAL 7016)

(Special colours available on request)

Packaging unit

13.00 kg, 6,0 kg

Minimum working temperature

- 5 °C

Temperature resistance

- 30°C to + 80°C

Cleaning in fresh condition

WIDOPAN-Cleaner

Storage

If container is kept closed and storage temperature held constantly below + 20°C the product may be used for up to 6 months

Range of applications

WIDOCRYL-Roller coating serves as coating for new constructions as well as for redevelopment of old buildings with anti-slip properties for floors, stairs, balconies and for marking walkways and traffic ways.

WIDOCRYL-Roller coating is certified for R11 (anti slip).

Application

The material basis of WIDOCRYL-Roller coating is a low viscous, elasticised methyl methacrylate resin. The Roller coating adheres to many surfaces with-out priming. The surface has to be dry, clean and free from grease and dust.

Tests should generally be made on curing and adhesion to the substrate.

Mixing

Before adding the hardener, the WIDOCRYL-Roller coating must be stirred thoroughly. Due to the low pot life, only small amounts should be mixed with the hardener. The amount of hardener depends on the temperature and is stated on the lid.

Further details, especially regarding hazard statements, security advices and measures in the event of fire can be found in the safety data sheet under sections 2, 4, 5, 6, 7 and 8.

Please also refer to our technical information sheets.