

## WIDOCRYL-Topsiegel PM



### Basis

Methyl methacrylate resin

### Curing with hardener (at + 20°C)

Rainproof after 30 min.

Walkable after 60 min.

### Consumption

Approx. 500 - 700 g/m<sup>2</sup>

### Basic colours

Window grey, light grey, pebble grey, ivory, light ivory, beige, oxide red (special colours on request)

### Packaging unit

10.00 kg, 5.00 kg

### Min. working temperature

-5°C

### Temperature resistance

-30°C to +80°C

### Cleaning in fresh condition

WIDOPAN-Cleaner

### Storage

If container is kept closed and storage temperature held constantly below +20°C, the product may be used for up to 6 months.

### Balconies, terraces, walkways

WIDOCRYL-Topsiegel PM is used as decorative topping on surfaces.

It may be used on waterproofings, primings and wearing layers from Widopan.

WIDOCRYL-Topsiegel PM is based on methyl methacrylate resin.

The surface to be sealed must be dry, clean and free from grease and dust.

### Flat roofs

WIDOCRYL-Topsiegel PM may also be used as decoration of surface seals of WIDOPAN-FD.

Please refer to our technical information sheets!

### Parking deck

WIDOCRYL-Topsiegel PM is used on parking decks and traffic areas to seal the wearing layer. Loose chippings must be removed before the Topsiegel PM is applied. Please check with our application engineering team for details on application and amounts required in each specific case.

### Mixing

WIDOCRYL-Topsiegel PM must be carefully stirred before adding the hardener. Because of the short working time, only fairly small amounts should be mixed with hardener.

The required amount of hardener depends on the temperature. For details see container lid.

Further details, especially regarding hazard statements, security advices and measures in the event of fire can be found in the safety data sheet under sections 2, 4, 5, 6, 7 and 8.

**Please also refer to our technical information sheets!**