

## WIDOPAN-Cfl Powder



### Basis

Ammonium polyphosphate

### Consumption

0,1 kg per 1 kg WIDOCRYL-Topsiegel or WIDOCRYL-Sealing PM (share of 10 %)

### Packaging unit

10 kg plastic bucket

### Colour

white

### Form

Powder, fine ground

### Storage

If container is kept closed and storage temperature held constantly between +15° and +20° C, the product may be used for up to 6 months.

WIDOPAN-Cfl powder is a flame retardant fire protection powder which is mixed into WIDOCRYL-Topsiegel or WIDOCRYL-Sealing PM. It is part of the WIDOPAN-Cfl S1 system which is applied as hardly flammable floor covering on balconies, arcades or escape and rescue routes. By mixing in the powder, the flame retardancy is reached.

### Application

For application, the powder will be mixed at a mixing ratio of 0,1 kg WIDOPAN-Cfl powder on 1 kg WIDOCRYL-Topsiegel or WIDOCRYL-Sealing PM. The powder needs to be mixed by machine with the resin until the powder has completely dissolved.

Mixing ratio in ml
<b>With WIDOCRYL-Topsiegel SV:</b>
1l WIDOCRYL-Topsiegel SV : 187,5 ml WIDOPAN-Cfl Powder (7,5 plane measuring spoons)
<b>With WIDOCRYL-Sealing PM:</b>
1l WIDOCRYL-Sealing PM : 175,0 ml WIDOPAN-Cfl Powder (7 plane measuring spoons)

Further details, especially regarding hazard statements, security advices and measures in the event of fire can be found in the safety data sheet under sections 2, 4, 5, 6, 7 and 8.

**Please also refer to our technical information!**