

## WIDOCRYL-Detail PG



### Basis

Urethane-modified methyl methacrylate resin (PMMA)

### Consumption (using the WIDOCRYL-PG OS 11a system)

Approx. 2,6 kg/m<sup>2</sup>

### Curing with hardener (at + 20,0 °C)

approx. 60 min.

### Packaging unit

25.00 kg

### Minimum working temperature

0° C

### Maximum working temperature

+35°C

### Pot life (at +20°C)

approx. 15 min.

### Cleaning in fresh condition

WIDOPAN-Cleaner

### Storage

If container is kept closed and storage temperature held constantly below 25°C, the product may be used for up to 6 months.

WIDOCRYL-Detail PG is a liquid waterproofing system used for waterproofing without reinforcement within the WIDOCRYL-PG OS 11a System. The material basis of WIDOCRYL-Detail PG is urethane-modified methyl methacrylate resin (PMMA).

The material can be applied after curing of the priming layer which depends on the surface. The surface to be waterproofed has to be dry, clean, free from grease and dust. WIDOCRYL-PG is then applied on the finished waterproofing layer.

### Mixing

Before adding the hardener, WIDOCRYL-Detail PG has to be stirred thoroughly. The amount of hardener depends on the temperature. The dosage is mentioned on the lid. All components should be stirred for at least 2 min. Due to the short pot life after the hardener has been added, we recommend to only mix small amounts.

### Application

WIDOCRYL-Detail PG is poured on the surface. It can be spread using a rubber blade or a squeegee and then rolled off with a paint roller.

Further details, especially regarding hazard statements, security advices and measures in the event of fire can be found in the safety data sheet under sections 2, 4, 5, 6, 7 and 8.

**Please also refer to our instructions on priming and to our technical information sheets!**