

Priming Guideline

WIDOSEAL-LF 1K for upstands on roofs, balconies and terraces, flat roofs and concrete components



| Subsoil, surfaces, material | Pre-treatment | Priming | Notes |
|---|---|----------------------|-------|
| Roof sheets | | | |
| | | | |
| EPDM -Roof sheets | Clean with WIDOPAN-Cleaner | No priming necessary | |
| FPO/TPO-Roof sheets | Frequently possible, tested roof sheets and how they need to be pre-treated can be enquired | | |
| Bitumen with slate | Brush the sheeting thoroughly | No priming necessary | |
| PVC- Roof sheets | Clean with WIDOPAN-Cleaner Mechanically roughen the surface. | WIDOPUR-Primer FTE | |
| EVA/VAE-Roof sheets | Frequently possible, tested roof sheets and how they need to be pre-treated can be enquired | | |
| Mineral surfaces | | | |
| | | | |
| Concrete, screed | The surface needs to be dry (max. ≤ 6 %) dampness), free from dust, sustainable, free from separating agents and other substances which lower the adhesion. | No priming necessary | |
| Dry stones e.g., lightweight concrete, Lime Sand, fiber ce-ment board | The surface needs to be dry (max. ≤ 6 %) dampness), free from dust, sustainable, free from separating agents and other substances which lower the adhesion | No priming necessary | |
| Metallic surfaces | | | |
| | | | |
| Copper | Degrease and clean with WIDOPAN-Cleaner MEK Mechanically roughen the surface. | No priming necessary | |
| Zinc, galvanised steel, stain-less steel, aluminium | Degrease and clean with WIDOPAN-Cleaner MEK Mechanically roughen the surface. | No priming necessary | |
| Lead | Degrease and clean with WIDOPAN-Cleaner MEK | No priming necessary | |
| | | | |
| Other | | | |
| | | | |
| Wood sawed, without chemical wood protection, OSB boards | The surface needs to be dry (max. ≤ 6 %) dampness), free from dust, sustainable, free from separating agents and other substances which lower the adhesion | No priming necessary | |
| Synthetic window- and door-frames | Clean with WIDOPAN-Cleaner | WIDOPUR-Primer FTE | |

Priming Guideline

WIDOSEAL-LF 1K for upstands on roofs, balconies and terraces, flat roofs and concrete components



| Subsoil, surfaces, material | Pre-treatment | Priming | Notes |
|-----------------------------|---------------|---------|-------|
|-----------------------------|---------------|---------|-------|

Additional fastening may be required for connections and edges (see professional rules for waterproofed roofs). Otherwise, manufacturer's specifications apply as well as all technical specifications from Widopan Produkte GmbH.

Further notes:

If required, send us a sample of the surface of at least 30 x 50 cm. We will then determine the optimal pre-treatment for the surface. Surfaces need to be free from dust and dry, free from loose parts and free from oil and grease.

Before and during the application of liquid waterproofing, please take care of the dew point (+3 °C) (refer to the dew point table). **You need to prevent moisture and moisture inclusion within the waterproofing.**